

Chemical Resistance Chart



The resistance of plasticised PVC, Nylon, Polyester Elastomer Lining, low density Polyethylene & Polyurethane to a wide range of chemicals is listed in the following table. The symbols used to denote performance are as follows:-

- ✓ Satisfactory
- Some attack or absorption: the material may be considered for use when alternative materials are unsatisfactory and where limited life is acceptable. When PVC is to be used with such chemicals fullscale trials under realistic conditions are particularly necessary.
- ✗ Unsatisfactory: so rated because of decomposition, solution, swelling, loss of ductility etc. of the samples tested.

In order to give guidance, the resistance of PVC to some chemicals has been predicted from its resistance to other chemicals which have a similar composition. Such predictions are shown using an asterisk (*) with the symbols listed above.

It may be safely assumed that chemical resistance decreases with both increasing temperature and with increasing concentration of reagent, and that the reverse is also true.

No valid assumptions can be made, however, if the temperature and concentration move in compensating directions. The rating 'some attack or absorption' (symbol - ■) should not be assumed to apply at conditions different from those shown.

- Chemical resistance of polyurethane hoses and composite hoses sleeved with polyurethane. The polyurethane is not recommended for continuous use in contact with water above 40°C (or solutions containing water above 40°C) because of its hydrolising effect. Hydrolysis can also occur with long exposure to:

- a) high humidity at elevated temperatures,
- b) acid and alkali solutions,
- c) aerated water,
- d) fungi and bacteria.

Some substances having a satisfactory rating may give swelling but this is usually minimal. The assumption should not be made that this indicates deterioration of the polyurethane.

Concentration		Plasticised PVC (PVC-P)		Nylon		Polyester Elastomer Lining		Polyethylene Low Density, LDP		Polyurethane	
		20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
acetaldehyde			✗ ^o	✓	✗			■	✗	✗ ^o	
	40% aq. solution		✗ ^o					■	✗		
	100%	✗ ^o	✗ ^o					■	✗		
acetic acid										■	●
	Dilute										
	10% aq. solution	✓		✓	■ ✗			✓	✓		
	20%					✓	✓ ^o				
	30%					✓	✓ ^o				
	50%			■ ✗	✗						
	60% aq. solution	✓	■					✓	✓		
	Higher concs.									✗ ^o	●
	Concentrated			■ ✗	✗						
	Glacial (conc.)	✗	✗	✗	✗	✓	■ ^o (? at 38°C)	■	✗	✗ ^o	
acetic anhydride		✗ ^o	✗ ^o	■	✗	✓ ^o		■	✗	✗ ^o	
acetone (dimethyl ketone)				✓	■	■	■ ^o	✗	✗	✗	
	Traces	✗	✗	✓	■	■	■ ^o				
	100%	✗	✗								
acetonitrile			✗ ^o								
acetophenone (methyl phenyl ketone)		✗ ^o	✗ ^o								
acetophenetidine		✓ ^o	✓ ^o								
acetylene gas				✓	✓	✓	✓ ^o			✓■	
adipic acid											
alcohol, allyl		✗ ^o	✗ ^o								
alcohol, amyl		✓									
alcohol, benzyl		✗ ^o	✗ ^o								
alcohol, butyl		✓									
alcohol, cetyl		✓ ^o	✓ ^o								
alcohol, dodecyl (dodecanol)		✓	✓ ^o								
alcohol, ethyl	40% w/w water	✓									
	100%	✓ ^o									
alcohol, furfuryl		✗ ^o									
alcohol, hexyl		✓									
alcohol, isopropyl		✓									
alcohol, lauryl		✓	✓								
alcohol, methyl	6% aq. solution	✓	✓								
	100%	■									
alcohol, nonyl (nonanol)		✓ ^o									
alcohol, octyl (octanol)		✓									
alcohol, propargyl		✓									
aliphatic hydrocarbons											
allyl chloride		✗ ^o	✗ ^o								
alum		✓	✓	✓ ^o	✓ ^o	✓ ^o		✓	✓	✓■	●
aluminium acetate		✓ ^o									
aluminium chloride		✓	✓	✓ ^o	✓ ^o	✓ ^o	✓ ^o	✓	✓	✓■	●
aluminium fluoride		✓ ^o									
aluminium hydroxide		✓									
aluminium nitrate		✓	✓ ^o								
aluminium oxalate		✓ ^o	✓ ^o								
aluminium oxychloride		✓ ^o									
aluminium potassium sulphate		✓	✓								
aluminium sulphate		✓ ^o	✓ ^o	✓ ^o	✓ ^o	✓ ^o	✓ ^o	✓	✓	✓■ ^o	●
ammonia	0.88 s.g. aq. solution										
	Anhydrous gas							✓	✓	✓■ ^o	
	Anhydrous liquid	✗ ^o	✗ ^o	✓	✓			✓	✓	■	
ammonia aqueous											
ammonium bicarbonate		✓ ^o	✓ ^o								
ammonium bifluoride		✓ ^o	✓ ^o								
ammonium carbonate		✓	✓ ^o								
ammonium chloride		✓	✓	✓ ^o	✓ ^o	✓	✓ ^o	✓	✓	✓■ ^o	●
ammonium fluoride		✓									
ammonium hydrosulphide		✓ ^o									
ammonium hydroxide		✓		✓	✓	✓ ^o	✓ ^o	✓	✓	✓■ ^o	●
	Dilute										
ammonium metaphosphate		✓ ^o	✓ ^o								
ammonium nitrate		✓	✓ ^o								
ammonium oxalate		✓	✓ ^o								
ammonium persulphate		✓ ^o	✓ ^o								
ammonium phosphate		✓ ^o	✓ ^o								
ammonium sulphate		✓	✓	✓	■	■	■ ^o	✓	✓	✓■ ^o	●
ammonium sulphide		✓	✗								
ammonium thiocyanate		✓	✓ ^o								
amyl acetate (pentyl acetate)		✗ ^o	✗ ^o	✓	✓	■		✗	✗	✗	
amyl alcohol				✓ ^o	✓■ ^o	✓		✓	✗	■	
amyl chloride (pentyl chloride)		✗ ^o	✗ ^o								
anethole											
aniline (amino benzene)		✗	✗	■	✗	✗	✗	■	✗ ^o	✗	
aniline hydrochloride		✗	✗ ^o								
aniline sulphate		✓									
animal oils		✓ ^o									
anthraquinone											
anthraquinone sulphonic acid											
antimony chloride		✓ ^o	✓ ^o								
antimony trichloride		✓ ^o	✓ ^o								
aqua regia	Dilute										
	Concentrated										
arcton 6 (refrigerant)								■			
arcton 11 (refrigerant)						✓ ^o				■	
arcton 12 (refrigerant)				✓		✓ ^o				■	
					(at 55°C)						
arcton 22 (refrigerant)				✓						■	
arcton 113 (refrigerant)				✗	✗					✗ ^o	
arcton 114 (refrigerant)						✓ ^o					
arsenic acid	Concentrated	✓	■								
arysulphonic acid			✗ ^o								
barium carbonate		✓ ^o	✓ ^o								
barium chloride		✓	✓ ^o	✓	✓	✓ ^o	✓ ^o	✓	✓	✓■	●
barium hydroxide		✓ ^o		✓	■	✓ ^o		✓	✓		
	Dilute									✓■ ^o	●
barium sulphate		✓ ^o	✓ ^o								

Concentration	Plasticised PVC (PVC-P)		Nylon		Polyester Elastomer Lining		Polyethylene Low Density, LDP		Polyurethane	
	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
barium sulphide	✓	✓								
beer			✓	✓	✓	✓	✓	✓	✓	●
benzaldehyde	Traces	✗ ^o	✓	✗	✓	✓	✗	✗	✗ ^o	
	100%	✗ ^o								
benzene	✗	✗	✓	■	■	✗ ^o	✗	✗	✗	
benzoic acid		✗ ^o								
benzoyl chloride	✗ ^o	✗ ^o								
benzyl acetate		✗ ^o								
benzyl alcohol			■	✗			✗	✗		
bismuth carbonate	✓ ^o	✓ ^o								
bleach (see calcium hypochlorite)										
borax (sodium tetraborate)	✓ ^o		✓ ^o	✓ ^o	✓	✓ ^o	✓	✓	✓ ^o	●
boric acid	✓ ^o		✓ ^o		✓	✓ ^o	✓	✓	✓■	●
boron trifluoride										
brine	✓ ^o	✓ ^o	✓	✓	✓ ^o	✓ ^o	✓	✓	✓	●
bromine	Traces, gas	✗ ^o								
	100% (dry gas)	✗ ^o	✗	✗			✗	✗		
	Liquid	✗ ^o	✗	✗	✗ ^o	✗ ^o	✗	✗		
butadiene										
butane			✓	✓	✓	✓ ^o	✓		✓■	
butanediol	✗ ^o	✗ ^o								
butyl acetate	✗	✗ ^o	✓	✓	■				✗	
butyl alcohol (butanol)			✓■	✗	✓ ^o		✓	✓ ^o	■	
butyl chloride	✗ ^o	✗ ^o								
butyl phenol										
butyraldehyde	✗ ^o	✗ ^o								
butyric acid							✗			
	20% aq. solution	✓ ^o								
	Concentrated	✗ ^o	✗ ^o							
calcium arsenate			✓	✓						
calcium bisulphite										
calcium carbonate										
calcium chlorate										
calcium chloride	Aq. solution	✓	✓	✓	✓	✓ ^o	✓	✓	✓■	●
	20% in methyl alcohol									
calcium hydroxide (lime solution)			✓ ^o		✓ ^o		✓	✓		
calcium hypochlorite	Dilute	✓					✓	✓	✓■	●
(chloride of lime, bleach)	Dilute		■ ^o						✓	●
	(5%)				✓					
calcium nitrate		✓ ^o								
calcium phosphate		✓ ^o								
calcium sulphate		✓ ^o								
carbitol acetate										
carbolic acid (phenol(s))			✗	✗	✗	✗	✗	✗	✗	✗
carbon dioxide	✓ ^o	✓ ^o	✓ ^o	✓ ^o	✓	✓ ^o	✓	✓	✓	✓
carbon disulphide	✗	✗	✓	✗	■	✗ ^o	✗	✗	■	✗
carbon monoxide	✓ ^o	✓ ^o								
carbon tetrachloride	✗	✗	✗	✗	✗	✗ ^o	✗	✗	✗	✗
carbonic acid	✓	✓ ^o								
casein	✓	✓ ^o								
castor oil	✓				■	■✗ ^o	✗	✗	✓ ^o	✓ ^o
chloracetic acid		✗ ^o								
chloral hydrate	✗ ^o	✗ ^o								
chloric acid										
chlorine	10% (dry gas)		✗	✗	✗ ^o	✗ ^o				
	100% (dry gas)		✗	✗	(Dry & Wet)	(Dry & Wet)	✗	✗	✗	✗
	10% (moist gas)									
chlorine trifluoride	✗ ^o	✗ ^o								
chlorine water	2%		✗	✗			✓	✓	✗	✗
	Sat. solution	■	✗ ^o				✓	✗		
chlorobenzene		✗								
chloroform	✗ ^o	✗ ^o	✗	✗	✗	✗	✗	✗	✗	✗
chlorosulphonic acid	✗ ^o	✗ ^o								
chrome alum (chrominium potassium sulphate)	✓	✓ ^o								
chromic acid									✗	✗
	Plating solution	✗	✗				✓	✓		
	10%		✗	✗			✓	✓		
cider			✓		✓ ^o		✓	✓	✓	●
citric acid	✓		✓	■	✓	✓ ^o	✓	✓		
	Dilute								✓■	●
coal gas			✓							
copper chloride	✓ ^o	✓ ^o								
copper cyanide	✓	✓								
copper fluoride	✓ ^o	✓ ^o								
copper nitrate	✓	✓ ^o								
copper sulphate	✓	✓ ^o	✓	✓	✓	✓ ^o	✓	✓	✓ ^o	●
creosote	✗	✗	✗ ^o	✗ ^o	✗ ^o	✗ ^o	✗	✗	✗	✗
cresols (inc. cresylic acid)	✗	✗	✗ ^o	✗ ^o	✗ ^o	✗ ^o	✗	✗	✗	✗
crotonaldehyde	✗ ^o	✗ ^o								
crude oil					✓ ^o		✗	✗	✓■	✓■ ^o
	Petroleum oil		✓	✓						
cupric chloride	✓	✓								
cupric fluoride	✓ ^o									
cupric nitrate	✓ ^o	✓ ^o								
cupric sulphate	✓	✓								
cyanide							✓	✓	✓■	●
cyclohexane			✓	■	✓		✗	✗	✗	
cyclohexanol	✗ ^o	✗ ^o								
cyclohexanone	✗ ^o	✗ ^o	✓	✗			✗	✗	✗	
d.d.t. preparation			✓							
decalin			✓	✓						
detergents, alkaline					✓ ^o	✓ ^o	✓ ^o	✓ ^o		
detergent, synthetic	✓ ^o				✓ ^o	✓ ^o	✓	✓	✓ ^o	●
developers, photographic	✓	✓ ^o								
dextrin (starch gum)	✓	✓ ^o	✓ ^o	✓ ^o	✓ ^o		✓	✓	✓ ^o	●
dextrose	✓ ^o	✓ ^o	✓ ^o	✓ ^o	✓ ^o	✓ ^o	✓	✓	✓ ^o	●
di acetone alcohol			✓	■						

Concentration	Plasticised PVC (PVC-P)		Nylon		Polyester Elastomer Lining		Polyethylene Low Density, LDP		Polyurethane	
	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
di ammonium phosphate			✓	■						
diamyl ether	✗ ^o	✗ ^o								
diazo salts	✗ ^o	✗ ^o	✓							
dibutyl phthalate	✗ ^o	✗ ^o	✓		✓		■	✗	■ ^o	
dichlorodifluoromethane										
dichlorethylene	✗ ^o	✗ ^o								
dichlorobenzene	✗ ^o	✗ ^o								
di chloro ethane			■							
di chloro methane			■							
di ethanolamine	20%		✓	■						
diesel oil			✓	✓■	✗ ^o	✗ ^o	■	✗ ^o	✓	✓
diethylene glycol	✓ ^o				✓ ^o	✓ ^o				
diethyl ether (ether)	✗ ^o	✗	✓				✗	✗	■	
diethyl ketone	✗ ^o	✗ ^o								
di isocyanate			✓ ^o							
dimethylamine										
dimethylcarbinol (isopropyl alcohol)	✓									
di methyl formamide ^o			✓						✗ ^o	
di methyl sulphoxide			✗	✗						
di octyl phosphate			✓	✓						
dioctyl phthalate	✗ ^o	✗ ^o	✓		✓		■	✗	■	
dioxane	✗	✗		✓						
disodium phosphate	✓ ^o	✓ ^o					✓	✓ ^o		
emulsifiers	✓ ^o	✓ ^o								
emulsions, photographic	✓ ^o	✓ ^o								
ethane										
ethyl acetate	✗ ^o	✗ ^o	✓	✓	■		■	✗	✗	✗
ethyl acrylate	✗ ^o	✗ ^o								
ethyl alcohol (ethanol)			✓■	✗	✓				■	✗
	40%						✓	✗		
	100%						✗	✗		
ethyl butyrate	✗ ^o	✗ ^o								
ethyl chloride	✗	✗ ^o								
ethyl ether			✓				✗	✗	■ ^o	
ethyl formate	✗ ^o	✗ ^o								
ethyl lactate	✗ ^o	✗ ^o								
ethyl sulphate										
ethylene bromide	✗ ^o	✗ ^o								
ethylene chlorhydrin			✗	✗						
ethylene chloride	✗ ^o	✗ ^o	■				✗	✗		
ethylene dibromide	✗ ^o	✗ ^o								
ethylene dichloride (dichloro ethane)	✗ ^o	✗ ^o	■		✗	✗	✗	✗		
ethylene glycol (glycol)	✓		✓	■	✓		✓	✓	■	
ethylene oxide	✗ ^o	✗ ^o	✓	■	✓		✓			
ethylene oxide										
fatty acids			✓	✓						
ferric chloride	■	■	✓		✓ ^o	✓ ^o	✓	✓	✓ ^o	●
ferric nitrate	✓ ^o	✓ ^o	✓							
ferric sulphate	✓	✓								
ferrous ammonium citrate	✓ ^o	✓ ^o								
ferrous chloride	■	■								
ferrous sulphate	✓	✓ ^o								
fixing solution, photographic	✓ ^o	✓ ^o								
flavours & essences			✓	✓	✓ ^o		✓ ^o		✓ ^o	●
fluorine	✗ ^o	✗ ^o	✗	✗	✓ ^o		■	✗		
fluosilicic acid										
formaldehyde	40% w/w in water	✓	✓	✗	■		✓	✓	■	
formic acid	3% aq. solution				■		✓	✓	✗	✗ ^o
	10% aq. solution						✓	✓		
	25% aq. solution						✓	✓		
	50% aq. solution						✓	✓		
	100%	✗ ^o	✗ ^o	✗	✗		✓	✓		
french polish			✓ ^o				✓		■	✗ ^o
freon 11 (refrigerant)			✓	■	✓ ^o				■	
freon 12 (refrigerant)			✓	■	✓ ^o				■	
freon 22 (refrigerant)			✓	■	✓ ^o				■	
freon 113 (refrigerant)			✓	■					✗ ^o	
	55°C				✓					
freon 114 (refrigerant)										
fructose	✓ ^o	✓ ^o								
fruit juice			✓		✓ ^o		✓	✓	✓ ^o	●
fruit pulp	✓	✓ ^o								
fuel oil			✓	✓■	✓ ^o	✓ ^o	■	✗	✓	■ ^o
furfural (furfuraldehyde)	✗ ^o	✗ ^o								
furfuryl alcohol			✓	■			✗	✗		
gallic acid	✓									
gas, coal or town - see coal gas										
gas, natural (mainly methane)- see natural gas										
gas oil			✓	■	✓ ^o		■	✗ ^o	✓■ ^o	
gaz (liquified petroleum gas)										
glacial acetic acid	✗	✗								
glucose	✓	✓ ^o	✓	✓	✓ ^o	✓ ^o	✓	✓	✓ ^o	●
glycerine	✓ ^o		✓	■	✓	✓ ^o	✓	✓	✓	
glycerol	✓ ^o									
glycerol monobenzyl ether	✗ ^o	✗ ^o								
glycol - see ethylene glycol										
glycolic acid										
grape sugar	✓ ^o	✓ ^o	✓	✓	✓ ^o	✓ ^o	✓	✓	✓ ^o	●
greases, general			✓	✓			■	✗ ^o	✓■ ^o	
greases, mineral			✓	✓	✓ ^o	✓ ^o	■	✗ ^o	✓	✓ ^o
ground nut oil			✓ ^o	✓ ^o	✓ ^o	✓ ^o	■	✗ ^o	✓	✓ ^o
heptane			✓				✗	✗	✓	
hexadecanol (cetyl alcohol)	✓ ^o	✓ ^o								
hexane			✓		✗	✗			✓ ^o	
hydrazine					✗	✗			✗ ^o	
hydrobromic acid	50% aq. solution	✓								
	100%	✓ ^o	✓ ^o							

		Plasticised PVC (PVC-P)		Nylon		Polyester Elastomer Lining		Polyethylene Low Density, LDP		Polyurethane	
Concentration		20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
hydrochloric acid	Dilute			✓	✗					✗✗ ^o	●
	1%			✓	✗						
	10% aq. solution	✓	✓	✓	✗			✓	✓		
	20%					■					
	22% aq. solution	✓	✓					✓	✓		
	37%					✗					
	Concentrated	✓	■	✗	✗			✓	✓	✗ ^o	✗ ^o
hydrocyanic acid											
hydrofluoric acid	Dilute									■ ^o	✗ ^o
	4% aq. solution	✓	✓					✓	✓		
	40% aq. solution	✓						✓	✓		
	48,75% and anhydrous					✗		✓	✓		
	60% aq. solution	✗	✗					✓	✓		
	Concentrated	✗	✗					✓	■		
hydro fluosilicic acid	20%			■							
	31%							✓ ^o	✓ ^o		
hydrogen		✓ ^o	✓ ^o	✓	✓	✓	✓ ^o	✓	✓	✓	✓ ^o
hydrogen bromide	Anhydrous	✓ ^o									
hydrogen chloride	Anhydrous	✓ ^o									
hydrogen fluoride	Anhydrous	✓ ^o									
hydrogen peroxide	3% (10 vol.)	✓						✓	✓		
	6% w/w (20 vols)			✓	✗			✓	✓		
	10%									■ ^o	
	12% (40 vol.)	✓						✓	✓		
	30% (100 vol.)	✓						✓	✓		
	90% and above	✓						✓	✓		
	90% and above							(Up to 90%)			
hydrogen phosphide (phosphine)		✓ ^o	✓ ^o								
hydrogen sulphide		✓									
hydroquinone		✓									
hydroxylamine sulphate											
hypochlorous acid		■	✗ ^o								
industrial methylated spirits (I.M.S.)				✓ ^o ■ ^o	✗ ^o	✓ ^o		■	✗	■	✗ ^o
iodine, tincture of										■ ^o ✗ ^o	✗ ^o
solution in potassium		✗ ^o	✗ ^o					✗	✗	■ ^o ✗ ^o	✗ ^o
iodide				✓ ^o				✗ ^o	✗ ^o		
iso cyanates		✗ ^o	✗ ^o								
isophorone				✓	✗	✓		✓		■ ^o	✗ ^o
iso propyl alcohol											
jet fuel				✓ ^o		✓		■ ^o	✗ ^o	■ ^o	
kerosene (paraffin oil)				✓	✓ ^o ■	✓ ^o	✓ ^o	■	✗		
lactic acid (dodecanoic acid)	Up to 40°C			✓	✓	✓ ^o				✓	■ ^o ✗ ^o
	10% aq. solution	✓		✓	✓			✓	✓	■ ^o	●
	100%	✗ ^o	✗ ^o					✓	✓		
lanoline		✓									
lauric acid		✓									
lauryl chloride											
lead acetate		✓ ^o	✓ ^o					✓	✓	✓ ^o ■ ^o	●
lead arsenate		✓ ^o	✓ ^o								
lead nitrate		✓ ^o	✓								
lead tetraethyl (see tetraethyl lead)		✓ ^o									
lime solution											
(see calcium hydroxide)											
linoleic acid											
linseed cake				✓	✓						
linseed oil				✓ ^o	✓ ^o	✓ ^o		■	✗	✓	✓ ^o
magnesium carbonate		✓ ^o	✓ ^o								
magnesium chloride		✓ ^o	✓ ^o			✓ ^o	✓ ^o	✓	✓	✓ ^o ■ ^o	●
	50%			✓	✓						
magnesium hydroxide	Dilute									✓ ^o ■ ^o	●
		✓ ^o	✓ ^o	✓		✓ ^o		✓	✓		
magnesium nitrate		✓ ^o	✓ ^o								
magnesium sulphate		✓ ^o	✓ ^o								
maleic acid	25% aq. solution										
	50% aq. solution										
	Concentrated		✗ ^o								
manganese sulphate		✓									
melamine acid - catalyst lacquers		✓ ^o	✓ ^o								
mercuric chloride		✗ ^o	✗ ^o								
mercuric cyanide		✓ ^o	✓ ^o								
mercurous nitrate		✓ ^o	✓ ^o								
mercury		✓ ^o	✓ ^o	✓	✓	✓	✓ ^o	✓	✓	✓ ^o	✓ ^o
mesityl oxide		✗ ^o	✗ ^o								
metallic soaps (water soluble)		✓ ^o									
methane				✓	✓					✓ ^o ■ ^o	
methyl acetate		✗	✗	✓	✓			✗	✗		
methyl alcohol (methanol)				✓	✗	✓				■	✗ ^o
	6%							✓	■ ^o	■	
	100%								■	✗	
methyl bromide		✗ ^o	✗ ^o	✓	✗						
methyl chloride (chloro methane)		✗ ^o	✗ ^o	✓	✗			✗	✗		
methyl cyclohexanone		✗ ^o	✗ ^o								
methyl ethyl ketone (M.E.K.)		✗ ^o	✗ ^o	✓	■	■		■	✗	✗	✗
methyl isobutyl ketone (M.I.B.K.)		✗ ^o	✗ ^o	✓	■	■ ^o		✗	✗	✗ ^o	✗ ^o
methyl methacrylate		✗ ^o	✗ ^o								
methyl sulphate		✗ ^o	✓	■							
methyl sulphonic acid											
methyl sulphuric acid	50% aq. solution										
	60% aq. solution										
	75% aq. solution										
	90% aq. solution										
methylated spirit				✓ ^o ■ ^o	✗ ^o	✓ ^o		■	✗	■	✗ ^o
methylene chloride		✗	✗	■	✗	✗	✗	✗	✗	✗ ^o	✗ ^o
(dichloro methane)											
milk		✓		✓	✓	✓ ^o		✓	✓	✓ ^o	●
mineral oils		✓	✗								
mixed acids (sulphuric /nitric)	Various proportions		✗ ^o								
molasses		✓	✓ ^o								

Concentration		Plasticised PVC (PVC-P)		Nylon		Polyester Elastomer Lining		Polyethylene Low Density, LDP		Polyurethane	
		20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
monochlorobenzene		✗	✗			✓ ^o		✓ ^o		✓ ^o	●
mustard				✓		✓ ^o		✓ ^o		■	✗ ^o
naphtha				✓	✓ ^o ■	✓ ^o		✓ ^o	✓ ^o	■	✗ ^o
naphthalen		✗ ^o	✗ ^o	✓	✓ ^o	■		✗	✗		
natural gas (mainly methane)				✓	✓ ^o					✓ ^o ■ ^o	
nickel chloride		✓ ^o	✓ ^o								
nickel nitrate		✓ ^o	✓ ^o								
nickel salts				✓				✓	✓	■ ^o	●
nickel sulphate		✓ ^o	✓ ^o								
nicotine											
nicotinic acid											
nitric acid	Dilute									■✗ ^o	●
	5% aq. solution	✓	✓					✓	✓		
	10% aq. solution	✓				■		✓	✓		
	25% aq. solution	✓				✗		✓	✓		
						(30% to conc.)					
	50% aq. solution	✓	■ ^o					■	✗		
	70% aq. solution	■	✗ ^o					■	✗		
	95% aq. solution	✗ ^o	✗ ^o					✗	✗		
	All concentrations			✗	✗						
	Concentrated									✗	✗
nitrobenzene		✗	✗								
nitrogen				✓ ^o		✓ ^o	✓ ^o	✓ ^o		✓	✓ ^o
nitropropane		✗	✗								
nitrous fumes	Moist		✗ ^o								
nitrous oxide gas											
oil, ASTM Oil No. 1						✓ (at 149_C)	✓			✓	✓ ^o ■ ^o
oil, ASTM Oil No. 3						✓ (at 149_C)	✓			✓	✓ ^o ■ ^o
oil, ASTM Ref. Fuel A						✓ (at 70_C)	✓			✓	✓ ^o ■ ^o
oil, ASTM Ref. Fuel B						✓ (at 70_C)	✓			✓	✓ ^o ■ ^o
oil, ASTM Ref. Fuel C						✓ (at 70_C)	■				
oil, animal						✓		■	✗	✓ ^o ■ ^o	✓ ^o ■ ^o
oil, crude - see crude oil											
oil, diesel - see diesel oil											
oil, etheral											
oil, fuel - see fuel oil											
oil, gas - see gas oil											
oil, hydraulic, petroleum base				✓						✓	(Mineral)
synthetic base				✓		✓				✗	✗
				Skydrol 500		Pydraul 312C			(Pydraul) (Skydrol 500)		
oil, mineral				✓	✓	✓	✓	✗	✗	✓	✓ ^o ■ ^o
(including common lubricating oils)											
oil, paraffin - see kerosene											
oil, transformer - see transformer oil											
oil, of turpentine - see turpentine											
oil, vegetable				✓	✓	✓		■	✗	✓	✓ ^o ■ ^o
oleic acid		✓		✓	✓	✓		✗	✗	■	
oxalic acid	10%	✓		✓	■			✓	✓		■ ^o
oxygen		✓ ^o	✓ ^o	✓	■			✓	✓ ^o	✓	
ozone		✓ ^o		■	✗			✗	✗	✓	
palmitic acid		✓ ^o									
paraffin		■									
penthane											
perchloric acid			✗ ^o								
perchloroethylene				■	✗	✗	✗	✗ ^o	✗ ^o	✗ ^o	✗ ^o
petrol											
petrol, aliphatic	2 star			✓	✓	✓		✗	✗	✓	
	3 star			✓	✓	✓		✗	✗	✓	
	4 star			✓	✓	✓		✗	✗	✓	
	5 star			✓	✓ ^o ■			✗	✗	✓	
	High Octane			✓	✓ ^o ■			✗	✗	✓ ^o ■	
petrol, aromatic (containing benzene)				✓ ^o	✓ ^o ■ ^o			✗	✗	✓ ^o ■ ^o	
petrol/benzene mixture	80:20 ratio	✗ ^o	✗ ^o								
petroleum ether		✗	✗	✓				✗	✗	■ ^o	
phenol (s) (carbolic acid)			✗ ^o	✗	✗	✗		✗	✗	✗	✗
phenylcarbinol (benyl alcohol)		✗	✗ ^o								
phenylhydrazine		✗ ^o	✗ ^o								
phenylhydrazine hydrochloride			✗								
phosgene	Gas										
	Liquid										
phosphates		✓ ^o	✓ ^o								
phosphoric acid	Dilute									■ ^o	●
	20% aq. solution	✓	✓								
	25%							✓	✓		
	30% aq. solution	✓	✓					✓	✓		
	50% aq. solution			✓	✗			✓	✓		
	90%										
	95% aq. solution										
phosphoric anhydride		✓ ^o									
phosphorus											
phosphorus pentoxide		✓ ^o		■				✓	✓		
phosphorus trichloride		✗ ^o	✗ ^o								
photographic developers		✓ ^o	✓ ^o								
photographic emulsions		✓ ^o	✓ ^o								
photographic fixing solutions		✓ ^o	✓ ^o								
phthalic anhydride		✓ ^o	✓ ^o								
picric acid (trinitro phenol)	1% w/w in water	✓ ^o	✓ ^o	■	✗			✓			
	10% w/w in alcohol	✓ ^o									
polyester emulsions				✓ ^o		✓ ^o					
polystyrene emulsions				✓ ^o		✓ ^o					
polyglycol ethers		✗ ^o	✗ ^o								
potassium acid sulphate		✓	✓								

[illegible]

Concentration	Plasticised PVC (PVC-P)		Nylon		Polyester Elastomer Lining		Polyethylene Low Density, LDP		Polyurethane	
	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
solvent naptha			✓	✓■	✓ ^o		■ ^o	✕ ^o	✓■ ^o	
stannic chloride	✓	✓								
stannous chloride	✓	✓								
starch	✓	✓ ^o								
steam - see water										
stearic acid	✓ ^o	✓ ^o	✓	✓	✓ ^o		✓	✓ ^o		
stearin (also stearine)			✓	✓			✓ ^o	✓ ^o		
styrene			✓	✓	✕ ^o	✕ ^o			■ ^o	
sucrose (cane or beet sugar)	✓ ^o	✓ ^o	✓ ^o	✓ ^o	✓ ^o	✓ ^o	✓	✓	✓ ^o	●
sulphamic acid			✕	✕						
sulphur			✓ ^o	✓ ^o					■ ^o	
sulphur dioxide	Colloidal						✓	✓		
	Molten				✓ ^o	✓ ^o				
	Gas & Liquid				✓ ^o					
	Dry	✓ ^o	✓ ^o				✓	✓		
	Moist		✕ ^o				✕	✕		
	Liquid		✕ ^o							
	10%		■	✕						
			■	✕			✕	✕		
sulphur trioxide										
sulphuric acid	Dilute								✓■ ^o	●
	1%		✓	■						
	10% aq. solution	✓	✓		✓		✓	✓		
	20% aq. solution	✓	✓		✓		✓	✓		
	30% aq. solution	✓	✓		✓		✓	✓		
	40% aq. solution	✓	✓		✓		✓	✓		
	45% aq. solution	✓	✓		✓		✓	✓		
	50% aq. solution	✓	■		✕		✓	✓		
	55% aq. solution		■		✕		✓	✓		
	60% aq. solution	■	■		✕		✓	✓		
	70% aq. solution	■			✕		✓	■		
	80% aq. solution				✕					
	90% aq. solution				✕					
	95% aq. solution				✕					
	98% aq. solution	✕	✕	✕	✕		■	✕		
	Fuming	✕	✕				✕	✕		
	Concentrated								✕ ^o	✕ ^o
sulphurous acid	10% aq. solution	✓								
	30% aq. solution	✓								
surface active agents (emulsifiers, (synthetic detergents & wetting agents)	All concentrations	✓ ^o	✓ ^o							
synthetic detergents	All concentrations	✓ ^o								
tallow		✓								
tannic acid		✓								
tanning extracts		✓ ^o								
tartaric acid		✓	✓	✓	✓ ^o				■ ^o	●
	Dilute									
	10%	✓ ^o	✓				✓	✓	■ ^o	●
tetra ethyl lead		✓ ^o								
tetrahydrofuran		✕ ^o	✕ ^o							
tetrahydronaphthalene		✕	✕							
tetralin		✕	✕							
thionyl chloride										
toluene	✕ ^o	✕ ^o	✓	■	■	✕	✕	✕	✕	✕
town gas - see coal gas										
transformer oil	✓	✕	✓ ^o				■	✕	■ ^o	■✕ ^o
tributyl phosphate	✕ ^o	✕ ^o	✓	✓	✓ ^o		■	✕ ^o	■	
trichloroacetic acid		✕ ^o								
trichloroethane	✕ ^o	✕ ^o	■	✕	✕ ^o	✕ ^o			✕ ^o	✕ ^o
trichloroethylene	✕ ^o	✕	■	✕	✕	✕	✕	✕	✕	✕
trichlorobenzene	✕ ^o	✕ ^o								
tricresyl phosphate	✕ ^o	✕ ^o	✓	✓			✕	✕	■✕ ^o	✕ ^o
triethanolamine	✓	✓								
triethylene glycol	✓ ^o									
trimethylamine										
trimethylpropane										
trisodium phosphate	✓	✓	✓	✓	✓		✓	✓	■ ^o	■✕ ^o
turpentine			✓	✓■	✓ ^o		■	✕	✓	■ ^o
turps substitute - see white spirit										
urea	✓ ^o									
urea, formaldehde soln.			✓ ^o		✓ ^o					
urea, soln.			✓	■	✓ ^o		✓	✓	✓■ ^o	
uric acid			✓	✓						
	Dilute				✓ ^o	✓ ^o	✓	✓		
		✓								
vegetable oils	✓									
vinegar	✓ ^o		✓	✓	✓		✓	✓	✓■	
vinyl acetate	✕ ^o	✕ ^o								
water - de ionized	✓	✓	✓	✓			✓	✓		
	100°C				■					
	70°C				✓	✓				
	40°C (up to)								✓	●
	110°C				✕					
steam	100°C		✕	✕	■		✕		✕	✕
water, sea - see sea water										
water, soda - see soda water										
wetting agents	All concentrations	✓ ^o	✓ ^o							
white spirit			✓	✓■	✓		■ ^o	✕ ^o	✓	■
wines and spirits			✓		✓		✓		✓	●
xylene (dimethyl benzene)	✕ ^o	✕ ^o	✓	■	■	■	✕ ^o	✕	✕	✕
xyleneol (dimethyl phenol)	✕	✕ ^o								
yeast	✓									
zinc ammonium carbonate	✓ ^o	✓ ^o								
zinc carbonate	✓ ^o	✓ ^o								
zinc chloride	✓ ^o	✓ ^o	✓	✓ ^o	✓	✓ ^o	✓	✓	✓■ ^o	●
zinc oxide	✓ ^o	✓ ^o								
zinc sulphide	✓	✓								